



TECHNICAL SPECIFICATION

Horizon Pulp & Paper Ltd.

100% Virgin Long Fibre SEMI-EXTENSIBLE Sack Kraft Paper

Produced in PM1/2 with maximum deckle 3660/3060 mm

No.	Term	Unit, SI System	Typical Value	Typical Value	Typical Value	SD	Standard
1.	Basis Grammage	g/m ²	120	130	140	+/-3 g/m ²	ISO 536
2.	Tensile Strength	KN/m					
		MD	8,0	8,7	9,4	7,5%	ISO 1924-3
		CD	5,4	5,9	6,3	7,5%	
3.	Stretch at Break	%					
		MD	6,0	6,0	6,0	5,0%	ISO 1924-3
		CD	7,0	7,0	7,0	7,5%	
4.	Tensile Energy Absorption (TEA)	J/m ²					
		MD	276	286	294	7,5%	ISO 1924-3
		CD	234	245	255	7,5%	
5.	Tensile Energy Absorption Index (TEA Index)	J/g					
		MD	2,3	2,2	2,1	7,5%	ISO 1924-3
		CD	1,95	1,9	1,85	7,5%	
6.	Tear Strength	mN					ISO 1974
		MD	1830	1985	2135	7,5%	
		CD	2250	2440	2625	7,5%	
7.	Wire Side Surface Water Absorption (COBB 60)	g/m ²	30	30	30	5,0%	ISO 535
8.	Porosity (Gurley)	s	16	16	16	10,0%	ISO 5636-5
9.	Moisture Content	% of weight	5,5-7,5	5,5-7,5	5,5-7,5		ISO 287

Values are tested at 23 °C and 50 % RH. Maximum limits by "Average-2SD"

Date of review: 07.07.2017