



# TECHNICAL SPECIFICATION

## Horizon Pulp & Paper Ltd.

Member of Tolaram Group – Singapore

### 100 % Virgin Long Fibre Fully-Extensible Sack Kraft Paper

Produced in PM1/2 with maximum deckle 3660/3060 mm

No.	Term	Unit, SI System	Value	Value	Value	Value	SD	Standard
1.	Basis Grammage	g/m <sup>2</sup>	70	80	90	100	+/-3 g/m <sup>2</sup>	ISO 536
2.	Tensile Strength	KN/m						
		MD	5,3	5,8	6,4	6,8	7,5%	ISO 1924-3
		CD	3,5	3,8	4,5	4,6	7,5%	
3.	Stretch at Break	%						
		MD	7,5	7,5	7,5	7,5	5,0%	ISO 1924-3
		CD	7,0	7,0	7,0	7,0	7,5%	
4.	Tensile Energy Absorption (TEA)	J/m <sup>2</sup>						
		MD	200	220	250	270	7,5%	ISO 1924-3
		CD	160	180	200	215	7,5%	
5.	Tensile Energy Absorption Index (TEA Index)	J/g						
		MD	2,9	2,8	2,8	2,7	7,5%	ISO 1924-3
		CD	2,3	2,2	2,2	2,1	7,5%	
6.	Tear Strength	mN						
		MD	1050	1200	1350	1510	7,5%	ISO 1974
		CD	1330	1520	1710	1890	7,5%	
7.	Wire Side Surface Water Absorption (COBB 60)	g/m <sup>2</sup>	30	30	30	30	5,0%	ISO 535
8.	Porosity (Gurley)	s	18	18	18	16	10,0%	ISO 5636-5
9.	Moisture Content	% of weight	5.5-7,5	5.5-7,5	5.5-7,5	5.5-7,5		ISO 287

Values are tested at 23 °C and 50 % RH. Maximum limits by "Average-2SD"

Date of review: 01.03.2022